



(11) **EP 0 982 274 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**01.03.2000 Bulletin 2000/09**

(51) Int. Cl.<sup>7</sup>: **C03C 8/24, C03C 8/04,  
H01M 8/02**

(21) Application number: **99113767.0**

(22) Date of filing: **14.07.1999**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventors:  
• **Kohli, Jeffrey T.**  
**SP TI 3-1 Corning NY 14831 (US)**  
• **Morena, Robert**  
**SP TI 3-1 Corning NY 14831 (US)**

(30) Priority: **14.08.1998 US 96559 P**


(74) Representative:  
**Behnisch, Werner, Dr. et al**  
**Reinhard-Skühra-Weise**  
**Friedrichstrasse 31**  
**80801 München (DE)**

(71) Applicant: **CORNING INCORPORATED**  
**Corning, N.Y. 14831 (US)**

(54) **Sealing frits**

(57) These sealing glass frits are a class of frits that seal in the intermediate temperature range of 600°-800°C. The frits are based on high strain point/high CTE

alkali-zinc-silicate glass compositions. The sealing frits are useful in planar solid oxide fuel cells (SOFC).



**EP 0 982 274 A2**

**Description****TECHNICAL FIELD**

5 **[0001]** This invention relates to sealing frits such as alkali-zinc silicate frits. More specifically, the frits are sealing frits for solid oxide fuel cells (SOFC).

**BACKGROUND ART**

10 **[0002]** Frits which seal in the temperature range of 600°-1000°C represent an intermediate class of materials between the B<sub>2</sub>O<sub>3</sub>- or P<sub>2</sub>O<sub>5</sub>-based frits used for low temperature sealing of many, commercial, glass products and the devitrifying frits used for high temperature joining of advanced, ceramic, structural components. The low temperature frits are used at temperatures below 600°C for sealing products such as cathode ray tubes (CRT), light bulbs and the like. The devitrifying high temperature frits are used at temperatures above 1,000°C to produce articles which may embody high temperature, fiber-reinforced, structural ceramics.

15 **[0003]** A very old product in the intermediate temperature range of sealing is a ZnO-B<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> frit. Another is a Li<sub>2</sub>O-modified, ZnO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub> frit designed for use between 900°-1,000°C. Frits that seal in the intermediate range of 600°-800°C are important in many industrial applications. The need for such frits became evident through requests for sealant frits for solid oxide fuel cells (SOFC).

**DISCLOSURE OF INVENTION**

20 **[0004]** In response to the demands of the market place, we have invented a class of alkali-zinc-silicate frits that produce seals in the intermediate temperature range of 600°-1000°C. These frits are high strain point/high CTE frits that are B<sub>2</sub>O<sub>3</sub> free. They have properties that make them especially useful for planar SOFC applications. These properties are:

- mechanical and chemical stability at 750°-800° during operation of the fuel cell;
- sealing temperature up to 1200° C.;
- effective barrier against the permeation of hydrogen gas; and
- 30 • CTE in the range of 100-120x10<sup>-7</sup>/°C.

**[0005]** The combination of high viscosity and high coefficients of thermal expansion (CTE) is a somewhat contradictory requirement for a glass composition. Most high temperature, sealing frits typically possess a combination of high viscosity and low CTE.

**BRIEF DESCRIPTION OF THE DRAWINGS****[0006]**

- 40 Fig. 1 is a perspective view of a stack of solid oxide fuel cells (SOFC).  
 Fig. 2 is an exploded, perspective view of the stack of SOFCs.  
 Fig. 3 is an exploded, fragmentary view of an SOFC.

**BRIEF MODE OF CARRYING OUT INVENTION**

45 **[0007]** Figs. 1 and 2 are perspective views of a typical SOFC. This SOFC consists of alternating, unit cells composed of layers of a solid electrolyte, cathode and anode plates. The solid electrolyte generally is yttrium (Y) - doped ZrO<sub>2</sub>.

**[0008]** Figs. 1 and 2 show SOFC 10 including stacked, unit cells 12. Unit cells 12 include anodes 14, cathodes 16 and an electrolyte (not shown).

50 **[0009]** Each cell 12 comprises distribution member 18 which embodies a plurality of parallel passages 20 for the supply of electrolyte, oxidant or fuel. The axes of passages 20 lie in a common plane.

**[0010]** Distribution member 18 is preferably manufactured from two, corrugated, ceramic plates. The corrugations of the plates are arranged parallel, and the troughs of one of the plates are bonded to the peaks of the other plate. This forms passages 20 which have a diameter on the order of 2mm.

55 **[0011]** Porous, support structure 22 surrounds and extends transversely of distribution member 18. It contacts the peaks and the troughs of member 18 to form a plurality of parallel passages which are anode 14 or cathode 16 chambers of solid oxide fuel cell stack 10. They provide the distribution and removal of the electrolyte for solid oxide fuel cells 10. The corrugated ceramic plates have apertures between passages 20 to allow fuel to flow from passages 20 into

anode 14 or cathode 16 chambers of solid oxide fuel cells 10.

[0012] Fig. 3 is an exploded, fragmentary view showing anodes 14 and cathodes 16 and their relationship to passages 20.

[0013] The glass frits of this invention may encapsulate each cell 12, or they may form a barrier between each cell 12. When forming a barrier, the glass frits will take the form of a plate sandwiched between adjacent cells 12. Structure 22 also may be made of the glass frits of this invention. The sealing frits prevent hydrogen gas from diffusing from one cell 12 to another.

[0014] The sealing frits of this invention do not contain  $B_2O_3$  and consist essentially of, by weight percent:

	Alkali-Zinc Silicate
$SiO_2$	50-70
$Al_2O_3$	0-5
$Li_2O$	0-5
$Na_2O$	2-10
$K_2O$	5-15
$ZnO$	10-25
$BaO$	0-10
$TiO_2$	0-5
$ZrO_2$	0-10

[0015] Preferably, the sealing frits consist essentially of, by weight:

	Alkali-Zinc Silicate
$SiO_2$	55-65
$Al_2O_3$	0-3
$Li_2O$	0-4
$Na_2O$	2-8
$K_2O$	5-10
$ZnO$	15-20
$BaO$	0-5
$TiO_2$	0-5
$ZrO_2$	0-6

[0016] The weight percents herein are calculated from the glass batch on an oxide basis. All temperatures herein are given in Celsius ( $^{\circ}C$ ).

#### Example

[0017] TABLE I shows several glass compositions for high strain point/high CTE glasses. The data shown are for three examples of alkali-zinc-silicate glass compositions. Each of the compositions was chosen for remaking as a frit because the values of softening point and CTE ( $RT-300^{\circ}$ ) reported for the bulk glass exceeded the minimum required values, respectively,  $650^{\circ}C$ . and  $90 \times 10^{-7}/^{\circ}C$ . After melting, each composition was made into a frit by dry ball-milling to a mean particle size of 10-20  $\mu m$ .

[0018] Small cylinders were then hand-pressed for the evaluation of flow performance. Bars for CTE and viscosity

measurements were made by pressing such shapes using a hydraulic press. All test specimens were fired to the indicated thermal cycle and then evaluated for properties. In the case of flow performance, a rating of "very good" meant that the frit flowed to such an extent that the initial, 12 mm diameter increased to at least 25 mm upon firing.

[0019] The alkali-zinc-silicate frits did not undergo any substantial crystallization prior to flow, and consequently exhibited substantial flow. The relatively good agreement between bulk glass and fired frit properties further indicates that the frit remained vitreous during the firing treatment.

[0020] The data in TABLE I show that these alkali-zinc-silicates are excellent sealing frits for many applications in the temperature range of 600°-1000°C. The data in TABLE I also indicate that the alkali-zinc-silicates have the potential for use in a solid oxide fuel cell. They have the desired CTE, but their softening points are marginal to meet the strict requirement of mechanical stability at 750°-800°. These compositions did serve, however, as the basis for attempts to increase viscosity through devitrification. Other potential applications for high CTE frits are coatings for bonding to a particular substrate at a temperature no greater than 1000°-1100°. This requirement puts an upper limit of the softening point of approximately 850°-900°.

TABLE I

Compositions for High Strain Point/High CTE Frits									
Weight Basis %									
	1	2	3	4	5	6	7	8	9
SiO <sub>2</sub>	62.2	58.9	58.9	60.0	62.2	58.7	59.8	59.4	56.3
Al <sub>2</sub> O <sub>3</sub>	1.6	1.5	1.5	1.5	1.6	1.5	1.5	2.0	1.9
Li <sub>2</sub> O	2.3	2.2	2.2	2.2	1.0	0.9	0.9	--	--
Na <sub>2</sub> O	4.7	4.5	4.5	4.6	7.5	7.1	7.3	7.7	7.3
K <sub>2</sub> O	7.2	6.8	6.8	6.9	7.1	6.8	6.9	11.7	11.1
ZnO	17.3	16.4	16.4	16.7	18.5	17.5	17.9	19.2	18.2
BaO	4.7	4.4	4.4	4.5	2.3	2.2	2.2	--	--
TiO <sub>2</sub>	--	--	--	3.5	--	--	3.5	--	--
ZrO <sub>2</sub>	--	5.3	5.3	--	--	5.3	--	--	5.2
Physical Properties									
Bulk Glasses (Annealed @ 575° C.)									
CTE (RT-300°)	89.2	82.0	83.1	87.0	93.7	89.0	91.8	104.5	97.6
Softening Pt., °C.	667	711	714	668	692	739	696	740	786
Frits (Sintered @ 800°/1 hr.)									
CTE (RT-500°)	106.8	-	92.5	-	-	93.6	-	-	101.3
Softening Pt., °C.	681	-	781	-	-	733	-	-	783

[0021] The R<sub>2</sub>O-ZnO-SiO<sub>2</sub> compositions set forth in TABLE I are illustrative of the present invention. Batches, based on these compositions were mixed, melted and poured in conventional manner to provide test pieces for measurement. Compositions 1, 5 and 8 are base compositions in which the ZnO content was gradually increased, typically at the expense of SiO<sub>2</sub> and/or total R<sub>2</sub>O. Also, Li<sub>2</sub>O was replaced by Na<sub>2</sub>O.

[0022] The remaining compositions (2-4, 6, 7 and 9) were formulated in an attempt to obtain an increased softening point by means of glass devitrification. Thus, a three mole % addition of a potential crystallization agent, selected from ZrO<sub>2</sub>, ZrSiO<sub>4</sub> and TiO<sub>2</sub>, was added to the batches of base glass compositions 1 5 and 8. The amounts are shown in weight % in TABLE I for consistency. ZrO<sub>2</sub> was added to composition 1 to form composition 2. ZrSiO<sub>4</sub> was added to compositions 1, 5 and 8 to form compositions 3, 6 and 9, respectively. TiO<sub>2</sub> was added to compositions 1 and 5 to form compositions 4 and 7, respectively.

[0023] TABLE I lists the measured CTE and softening point for each composition in bulk glass form, after first anneal-

ing at 575° C. In addition, properties are also listed for several of the glasses after they were made into frits. These glasses were ball-milled to a 15-20  $\mu\text{m}$  powder, dry-pressed into a disk or bar, sintered at 800° C. for one hour, and then sawed or drilled into the required shape for the property measurement.

[0024] The data in TABLE I indicate that the are higher in softening point than the initial additive-free compositions. Within each of the three sets, the highest softening point was attained with 3 mole % addition of  $\text{ZrSiO}_4$  to the initial frit. The three  $\text{ZrSiO}_4$ -containing compositions (#s 3, 6 and 9) were ball-milled so that properties could be determined on them as frit batch. Also included in this study were the parent base frits. As frits, all three of the compositions were significantly higher in softening point than was the initial frit. Of the three compositions to which  $\text{ZrSiO}_4$  was added, composition 9 in TABLE I, with the CTE of  $101.3 \times 10^{-7}/^\circ\text{C}$ ., was preferred.

[0025] In an effort to provide higher temperature sealing materials for use as fuel cell sealants, potential crystallization catalysts were also blended into samples of the composition 9 frit as mill additions. The crystallization catalysts selected for blending were zirconia and alumina. The zirconia used had a mean particle size of approximately 3-5  $\mu\text{m}$ . The alumina used was a reactive aluminum oxide with a mean particle size < 0.5  $\mu\text{m}$ , although there is good reason to believe that other commercial aluminas could as well be used for this purpose.

[0026] The samples were ball-milled to a mean particle size of 15-20  $\mu\text{m}$ , and then blended on a 90:10 proportion (wt. basis) with the zirconia, and the alumina, mill additions. Flow buttons were made from these mixtures by hand-pressing 5g of powder into small cylinders (1.25 cm diam. x 2.5 cm tall) and firing at 1000° C. for one hour. Also included was a flow button of frit powder without any mill addition (straight frit). After firing, the flow properties of the mixtures, and of the straight frit, were compared to obtain a qualitative estimate of frit viscosity. Both the straight frit and the zirconia blend showed substantial flow during the 1000° C. firing. This indicated that, at the particular loading level and/or particle size employed, zirconia did not increase viscosity as well as alumina. The flow button for the alumina mixture was, by contrast to the zirconia blend, well-sintered. Only moderate slumping took place during the 1000° C. firing.

[0027] X-ray diffraction data were obtained from runs made on fired, frit bodies containing alumina as a mill addition. These data indicated that leucite ( $\text{K}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot 4\text{SiO}_2$ ), a compound having a high CTE, was formed during firing.

[0028] TABLE II sets forth several potential sealing materials for which comparative properties are recorded. Materials A and B were based on composition 9 of TABLE I, that is, without any mill additions. Materials C through F represent blends of composition 9 with varying amounts of the reactive alumina as a mill addition. The ratio of the glass of composition 9 to alumina in weight % is shown for each material.

[0029] Shown are the composition, the sintering temperature, the relative amount of flow, the measured CTE, and the softening point for each sintered blend. The sintered blends made with levels  $\geq 10\%$  appeared decidedly crystalline. The softening point increased for all levels of addition.

[0030] The CTE increased with increasing addition, except for the 95:5 blend containing 5% by weight  $\text{Al}_2\text{O}_3$ . The decreased CTE for this blend indicates that the presumed crystallization mechanism does not occur at this low a level of alumina addition. Rather, the lowered expansion, expected from a rule-of-mixture standpoint with the addition of alumina having a CTE of  $70 \times 10^{-7}/^\circ\text{C}$ ., occurs.

[0031] One blend with 10% loading, Example D in TABLE II, appears especially attractive as a sealing frit for solid oxide fuel cells. RT as used herein is room temperature at about 25° C.

[0032] Examples E and F indicate that, while the present frits are mid-temperature frits, they may become useful at higher sealing temperatures with the alumina mill addition.

TABLE II

Properties of Alumina Blends					
Ex	Composition Weight Basis	Firing Schedule	Flow Behavior	CTE, RT- 500	Softening Point
A	100 # 9	1000°/1 hr.	melted	-	-
B	100 # 9	800°/1 hr.	excellent	101.3	783°
C	95% # 9 5% $\text{Al}_2\text{O}_3$	800°/1 hr.	excellent	95.5	801°
D	90% # 9 10% $\text{Al}_2\text{O}_3$	1000°/1 hr.	slumped	101.7	837°
E	85% # 9 15% $\text{Al}_2\text{O}_3$	1100°/1 hr.	none well-sintered	107.8	crystalline (> 1150°)
F	80% # 9 20% $\text{Al}_2\text{O}_3$	1150°/1 hr.	none well-sintered	113.7	crystalline (1150°)

[0033] Although the now preferred embodiments of the invention have been set forth, it will be apparent to those skilled in the art that various changes and modifications may be made thereto without departing from the spirit and

scope of the invention as set forth in the following claims.

# Claims

- 5      **1.** Alkali-zinc-silicate sealing frits which seal in an intermediate temperature range having a composition consisting essentially of, by weight percent:

10

	Weight Percent
SiO <sub>2</sub>	50-70
Al <sub>2</sub> O <sub>3</sub>	0-5
Li <sub>2</sub> O	0-6
Na <sub>2</sub> O	2-10
K <sub>2</sub> O	5-15
ZnO	10-25
BaO	0-10
TiO <sub>2</sub>	0-5
ZrO <sub>2</sub>	0-10

15

20

- 25      **2.** Sealing frits according to claim 1 wherein the composition consists essentially of, by weight percent:

30

	Weight Percent
SiO <sub>2</sub>	55-65
Al <sub>2</sub> O <sub>3</sub>	0-3
Li <sub>2</sub> O	0-4
Na <sub>2</sub> O	2-8
K <sub>2</sub> O	6-12
ZnO	15-20
BaO	0-5
TiO <sub>2</sub>	0-5
ZrO <sub>2</sub>	0-6

35

40

- 45      **3.** Sealing frits according to claim 1 wherein the composition contains, as an addition to the composition, a crystallization agent selected from the group consisting of TiO<sub>2</sub>, ZrO<sub>2</sub>, and ZrSiO<sub>4</sub>.

- 50      **4.** Sealing frits according to claim 3 wherein the selected crystallization agent is ZrSiO<sub>4</sub>.

- 5(7).** Sealing frits according to claim 1 having a high viscosity and a high CTE.

- 6(9).** A sealing material that is a blend of an alkali-zinc-silicate sealing frit according to claim 1 and a mill addition selected from zirconia and alumina.

- 55      **7(11).** A sealing material according to claim 6 wherein the mill addition is a reactive alumina having a mean particle size less than 0.5 μm.





## EP 0 982 274 A2

**8(12).** A sealing material according to claim 6 wherein the mill addition is up to about 20% by weight of the sealing material.

**9(14).** Solid oxide fuel cells sealed with the sealing frits of claim 1.

**10(15).** A solid oxide fuel cell in accordance with claim 9 wherein the seal provides an effective barrier against hydrogen gas permeation.







FIG. 3





(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 982 274 A3**

(12)

**EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
02.08.2000 Bulletin 2000/31

(51) Int. Cl.<sup>7</sup>: **C03C 8/24**, C03C 8/04,  
H01M 8/02

(43) Date of publication A2:  
01.03.2000 Bulletin 2000/09

(21) Application number: 99113767.0

(22) Date of filing: 14.07.1999

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventors:  
• Kohli, Jeffrey T.  
SP TI 3-1 Corning NY 14831 (US)  
• Morena, Robert  
SP TI 3-1 Corning NY 14831 (US)

(30) Priority: 14.08.1998 US 96559 P


(71) Applicant: CORNING INCORPORATED  
Corning, N.Y. 14831 (US)

(74) Representative:  
Behnisch, Werner, Dr. et al  
Reinhard-Skühra-Weise  
Friedrichstrasse 31  
80801 München (DE)

**(54) Sealing frits**

(57) These sealing glass frits are a class of frits that seal in the intermediate temperature range of 600°-800°C. The frits are based on high strain point/high CTE

alkali-zinc-silicate glass compositions. The sealing frits are useful in planar solid oxide fuel cells (SOFC).



**EP 0 982 274 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 99 11 3767

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	JP 63 035465 A (NIPPON ELECTRIC GLASS CO) 16 February 1988 (1988-02-16) * example 5 *	1	C03C8/24 C03C8/04 H01M8/02
X	DATABASE WPI Section Ch, Week 198812 Derwent Publications Ltd., London, GB; Class L01, AN 1988-081732 XP002139657 & JP 63 035465 A (NIPPON ELECTRIC GLASS CO), 16 February 1988 (1988-02-16) * abstract *	1	
A	US 5 453 331 A (BLOOM IRA D ET AL) 26 September 1995 (1995-09-26) * the whole document *	1-10	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C03C H01M
The present search report has been drawn up for all claims			
Place of search <b>MUNICH</b>		Date of completion of the search <b>7 June 2000</b>	Examiner <b>Somann, K</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (Pnc01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 11 3767

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

07-06-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 63035465 A	16-02-1988	JP 1921998 C	07-04-1995
		JP 6051579 B	06-07-1994
US 5453331 A	26-09-1995	AU 3364695 A	07-03-1996
		WO 9605626 A	22-02-1996

EPO FORM P4489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

